

LUCENETM LC161X

Polyolefin Elastomer for Polymer Modification

- Applications**
- General purpose thermoplastic elastomers, Polymer modification
 - Soft and hard TPO compounds

- Performance**
- Improved impact strength in polypropylene
 - Excellent filler acceptance
 - Available as pellet form
 - Outstanding toughness with flexible performance
 - Reduction of product weight

Resin Properties	Test methods	Units	Values ⁽¹⁾
Melt Index, 2.16kg/190 °C	ASTM D 1238	g/10min	0.5
Density @ 23 °C	ASTM D 1505	g/cm ³	0.868
Mooney viscosity, ML ₁₊₄ @ 121 °C	ASTM D 1646	MU	35

Physical Properties	Test methods	Units	Values ⁽²⁾
Tensile Strength @ Break	ASTM D 638 ⁽³⁾	MPa	9.4
Elongation @ Break	ASTM D 638 ⁽³⁾	%	>900
Flexural Modulus, 1%	ASTM D 790	Mpa	13
Hardness, Shore A	ASTM D 2240	-	67
Tear Strength, Type C	ASTM D 624	kN/m	38

Thermal Properties	Test methods	Units	Values
Melting Point, DSC	LG Method	°C	54
Glass Transition Temperature	LG Method	°C	-53

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 508 mm/min.